YIBIN BONAVEL NEW BUILDING MATERIALS CO., LTD

TEST REPORT

SCOPE OF WORK
FLEXIBLE STONE


REPORT NUMBER
260318008SHF-001

TEST DATE(S)
2026-03-18 - 2026-03-27

ORIGINAL ISSUE DATE
2026-03-31

PAGES
7

DOCUMENT CONTROL NUMBER
LFT-APAC-SHF-OP-10k(January 13, 2025)
© 2025 INTERTEK



Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch

Test Report

Statement

1.This report is invalid without company's special seal for testing on the assigned page.

2.This report is invalid without an authorized person's signature.

3.This report is invalid if altered.

4.Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Don't copy this report in partial without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.

5.This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

6.Except for the obligation, responsibility and liability (if any) for the appropriateness and professionality of afore-mentioned testing itself within the scope and amount of the testing fee received, Intertek does not and will not accept any other obligation or liability.

7.If the Client has any questions about the test results, Intertek B&C should be informed within the storage period of the samples. The sample storage period ends 5 working days after the offical report issue date. Samples of certification program are retained for the period required by the certification rules. The samples storage period shall be calculated according to the issue date of the original report in the case of quoting results and modifying reports.

8.Intertek B&C will service this report for the entire test record retention period. The test record retention period ends 6 years after this report original issue date. The test record retention period for certification program is 10 years. Test records and other pertinent project documentation will be retained for the entire test record retention period.

9.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch
Plant 5 & 11(4F), No. 6958 Daye Road, Fengxian District, Shanghai, China
Tel: +86 21-61136116 Fax: 021-61189921
Website: www.intertek.com

Test Report

Original Issue Date: 2026-03-31 Intertek Report No. 260318008SHF-001

Applicant: YIBIN BONAVEL NEW BUILDING MATERIALS CO., LTD

Address: Changning district, Yibin city, Sichuan province, China

Attn: Elaine

Manufacturer: YIBIN BONAVEL NEW BUILDING MATERIALS CO., LTD

Address: Changning district, Yibin city, Sichuan province, China

Test Type: Performance test, samples provided by the applicant.

Product Information

Product Name	Model	Specification	Brand
FLEXIBLE STONE	/	/	BONAVEL
Sample ID	**Sample Amount**	**Sample Received Date**	
S260318008SHF.001~003	13 pcs	2026-03-05, 2026-03-09, 2026-03-12	
Sample Description			
The sample consists of one package of inorganic material, one roll of fiberglass, and some complete panels with a thickness of about 3 mm. See the sample photo in Appendix A.			

Test Methods And Standards

Test Standard	EN 13823:2020+A1:2022 and EN ISO 1716:2010
Specification Standard	EN 13501-1:2018
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report does not involve sampling. The report only reflects conformity of the tested items of the samples provided by the testing applicant. Representativeness and authenticity of the submitted samples are responsibilities of the testing applicant.

2.The heat of combustion test section in this report only reflects the testing result based on the data and information followed the Δ mark provided by the testing applicant. The testing applicant agrees that Intertek has no duty, responsibility or obligation including without limitation examination, review, analysis, assessment, comment, suggestion, adjustment, calibration, modification, revision, guarantee or otherwise in regard to the legitimacy, compliance, applicability, adequacy, necessity, reasonableness, accuracy, appropriateness, reliability or any other feature or aspect of the data and information.

Report Authorized

Sally Xie Stone. Shi

Name: Sally Xie Name: Stone Shi

Title: Reviewer Title: Project Engineer

intertek
Total Quality. Assured.

Test Report

Original Issue Date: 2026-03-31 Intertek Report No. 260318008SHF-001

Test Items, Method and Results:

EN 13501-1:2018 Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests

1.1 HEAT OF COMBUSTION TEST

The test was conducted in accordance with EN ISO 1716. This test evaluates the gross heat of combustion (Q_{PCS}) of products at constant volume in a bomb calorimeter.

1.2 SINGLE BURNING ITEM TEST

The test was conducted in accordance with EN 13823. This test evaluates the potential contribution of a product to the development of a fire, under a fire situation simulating a single burning item near to the product.

1.3 CLASSIFICATION CRITERIA

The classification was determined in accordance with EN 13501-1:2018. The class A2 with its corresponding fire performance is given in the table below.

Table - Class of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products.

Class	Test Method(s)	Classification criteria	Additional classifications
A2	EN ISO 1716 and	PCS ≤3.0 MJ/kg [a] and PCS ≤4.0 MJ/m^2 [b] and PCS ≤4.0 MJ/m^2 [c] and PCS ≤3.0 MJ/kg [d]	--
	EN 13823	$FIGRA_{0.2MJ}$ ≤ 120 W/s and LFS < edge of specimen and THR_{600s} ≤ 7.5 MJ	Smoke production [e] and Flaming droplets/particles [f]

Note:

a. For homogeneous products and substantial components of non-homogeneous products.
b. For any external non-substantial component of non-homogeneous products.
c. For any internal non-substantial component of non-homogeneous products.
d. For the product as a whole.
e. s1 = SMOGRA ≤ 30m^2/s^2 and TSP_{600s} ≤ 50m^2; s2 = SMOGRA ≤ 180m^2/s^2 and TSP_{600s} ≤ 200m^2; s3 = not s1 or s2.
f. d0 = no flaming droplets/particles in EN 13823 within 600s;
d1 = no flaming droplets/particles persisting longer than 10s in EN 13823 within 600s;
d2 = not d0 or d1.

Test Report

Original Issue Date: 2026-03-31 Intertek Report No. 260318008SHF-001

Test Items, Method and Results:

2 RESULTS AND OBSERATIONS

Method	Parameter		Result
EN ISO 1716:2010	PCS	Inorganic layer, MJ/kg	0.8040
		Glass fibre (Layer No.2+3), MJ/m^2	0.9666
		The Whole Product, MJ/kg	0.9762
EN 13823:2020+A1:2022	$FIGRA_{0.2MJ}$, W/s		43.0
	THR_{600s} , MJ		0.655
	LFS, m		<Edge of specimen
	SMOGRA, m^2/s^2		11.1
	TSP_{600s}, m^2		46.5
	Flaming droplets/particles		No flaming droplets/particles occur within 600s

Note

1. Per EN 13823, the samples were fixed mechanically to the substrate. Substrate was a 12mm thick calcium silicate board. The density of the calcium silicate board was 850kg/m^3.

ΔThe information of each component of the product was declared by applicant, see below table.

Layer No. (from face to back)	Material of each Layer	Mass per unit area (kg/m^2)	Thickness (mm)
1	Inorganic layer	3.8	3
2	Glass fibre	0.16	0.25
3	Glass fibre	0.16	0.25

3 CLASSIFICATION

The classification has been carried out in accordance with EN 13501-1.

Fire behaviour		Smoke production			Flaming Droplets	
A2	-	s	*1*	-	d	*0*

Reaction to fire classification: *A2 - s1, d0*

Test Report

Original Issue Date: 2026-03-31 Intertek Report No. 260318008SHF-001

Test Items, Method and Results:

4 Test Photos of EN 13823



Before test (Long wing)



Before test (Short wing)



After test (Long wing)




After test (Short wing)


Test Report

Original Issue Date: 2026-03-31 Intertek Report No. 260318008SHF-001

Appendix A: Sample Received Photo



Front view (test side)



Back view



Glass fibre



Inorganic layer

Revision:

NO.	Date	Changes
260318008SHF-001	2026-03-31	First issue